

68 International Fonteway Chicksofte, TN 1 × 1 × 5 agt 934,552,8480 pre 931,852,853

TF Zinc Granules PRODUCT SPECIFICATIONS

Property	Specification	Typical
Total Zinc (% minimum)	99	99.5
Metallic Zinc (% minimum)	97	98
Iron (% maximum)	0.002	0.0003
Lead (% maximum)	0.002	0.0015
Copper (% maximum)	0.001	0.0005
Cadmium (% maximum)	0.0005	0.0001
Zinc Oxide	Balance	Balance
% Retained on 100 mesh sieve	0 - 20	15
% Retained on 200 mesh sieve	20 - 60	55
% Retained on 325 mesh sieve	20 - 55	27
% Through a 325 mesh sieve	0 - 15	3

APPLICATIONS

- Reducing agent
- Thread compounds
- · Precipitating agent
- Purification Applications

NOTE: All Purity Zinc Metals, LLC zinc oversizes are produced from 99.995% pure zinc metal. Zinc oversize grades are manufactured under license from Purity Zinc MetalsTM a Division of North American Zinc Company.

We believe the information herein to be reliable but we assume no responsibility for its accuracy. It will be the users responsibility exclusively to determine the suitability for these grades for the product manufactured by the user.