



PURITY ZINC METALS, LLC
298 International Boulevard
Chickasaw, TX
75824
931.552.8086
fax 931.552.5588
www.purityzinc.com

UltraPure[®] grades meet ASTM D520 Type III Specification for Zinc Dust Pigment

UP6 PRODUCT SPECIFICATIONS

Property	Specification	Typical
Total Zinc (% minimum)	99	99.5
Metallic Zinc (% minimum)	97	97.3
Iron (% maximum)	0.002	0.0003
Lead (% maximum)	0.002	0.0015
Copper (% maximum)	0.001	0.0005
Cadmium (% maximum)	0.0005	0.0001
Zinc Oxide	Balance	Balance
Average Particle Size*	5.0 - 8.0	6.5
Retained on 100 mesh screen (% max)	Nil	Nil
Retained on 200 mesh screen (% max)	0.2	0.08
Retained on 325 mesh screen (% max)	3.0	2.2
Specific Gravity	7.0 - 7.1	

* Air Permeability Method

APPLICATIONS

Coatings: Organic and inorganic
Reducing agent
Thread compounds
Precipitating agent
Purification Applications
Zinc Plating

NOTE: All Purity Zinc Metals, LLC UltraPure[®] dusts are produced from 99.995% pure zinc metal.
UltraPure[®] grades of zinc dust are manufactured under license from Purity Zinc Metals[™] a Division of North American Zinc Company.

We believe the information herein to be reliable but we assume no responsibility for its accuracy. It will be the users responsibility exclusively to determine the suitability for these grades for the product manufactured by the user.