

Make the wise choice...



ALLOY No. 93

For Slush Casting

Aluminum	5.10-5.25
Magnesium	0.005
Iron	.075 (Max.)
Lead	.003 (Max.)
Copper	0.10 (Max.)
Cadmium	.002 (Max.)
Tin	.002 (Max.)
Zinc	Balance

Note:

HIGH ALUMINUM AND OTHER SPECIAL ALLOYS MADE TO CUSTOMER SPECIFICATION

OTHER FORMS OF ZINC AVAILABLE

For Platers:

Zinc Flat Top Anodes
Zinc Slabs (50 lbs.)
Zinc Dust for Mechanical Plating and Galvanizing

For Galvanizers:

Prime Western Grade Zinc Slabs or Jumbos
90-10 Brightener Alloy
Other Special Steel Mill Alloys

290 Arvin Avenue
Stoney Creek, Ont. Canada
L8E 2M1
905-662-4802
Fax: 905-664-3944

498 International Boulevard
Clarksville, Tennessee 37040
931-552-8080
Fax: 931-552-5588

e-mail: sales@purityzinc.com